46

WILLOW

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufted 1/12” Loop Tufté 1/12” Bouclé Getuftet 1/12” Schlinge Getuft 1/12” Luspool
PILE MATERIAL COUCHE D’USURE POLMATERIAL POOLMATERIAAL	100% ECONYL® yarn 100% regenerated solution dyed nylon
SECONDARY BACKING DOSSIER RÜCKENAUSSTATTUNG RUG	Back2Back: Modified bitumen enhanced with a thermoplastic elastomer, reinforced with a glass fibre fleece covered with 100% PES fleece. 10% recycled content included
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	Ca. 4600g/m² Ca. 135,7 oz./yd²
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	Ca. 880 g/m² Ca. 25,9 oz./yd²
PILE ABOVE BACKING POIDS DE VELOURS UTILE POLNUTZSCHICHTGEWICHT NUTTIG POOLGEWICHT	Ca. 630 g/m² Ca. 18,6 oz./yd²
TOTAL HEIGHT EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	Ca. 7,8 mm Ca. 0,31”
PILE HEIGHT EPAISSEUR DU VELOURS POLDICKE POOLHOOGTE	Ca. 4,3 mm Ca. 0,17”
PILE DENSITY DENSITÉ DU VELOURS POLROHDICHTE POOLDICHTHEID	Ca. 0,146 g/cm³ Ca. 3 937 oz/yd³
TUFT DENSITY NOMBRE DE TOUFFES NOPPENZAHL AANTAL PUNTEN	Ca. 225.000 /m² Ca. 188.127 /yd²
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 33 - LC2
CASTOR CHAIR SUITABILITY EMPLOI CHAISE À ROULETTES STUHLROLLENEIGNUNG ROLSTOELGESCHIKTHEID	EN 985 A : continuous use
DONNÉES ENVIRONNEMENTALES	Démarche HQE® : cf. FDES suivant NF P01-010 Déclaration du 30/07/2003

FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1: B_{fl}-s1 ASTM E-648: Class 1
FASTNESS TO LIGHT SOLIDITÉ À LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	ISO 105-B02 ≥7
RUBBING FASTNESS SOLIDITÉ AU FROTTEMENT REIBECHTHEIT WRIJFECHTHEID	EN ISO 105-X12 ≥4
COLOUR FASTNESS TO WATER SOLIDITÉ À L’EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥4
THERMAL RESISTANCE RÉSISTANCE THERMIQUE WÄRMEDURCHLABWIDERSTAND WARMTEDOORLAATWEERSTAND	ISO 8302 0.086 m²K/W
IMPACT NOISE RATING ISOLATION PHONIQUE TRITTSCHALLVERBESSERUNGMAB GELUIDSISOLATIE	ISO 10140 ΔL: 36 dB (1 000 Hz) ΔL_w: 27 dB
SOUND ABSORPTION ABSORPTION PHONIQUE SCHALLABSORPTIONSGRAD GELUIDSABSORPTIE	ISO 354 α_w: 0,15 Hz 125 250 500 1000 2000 4000 α_s 0.00 0.06 0.08 0.19 0.37 0.47
PERMANENT ANTISTATIC ANTISTATIQUE PERMANENT PERMANENT ANTISTATISCH PERMANENT ANTISTATISCH	ISO 6356 ≤ 2 kV
TRANSVERSAL RESISTANCE RÉSISTANCE TRANSVERSALE DURCHGANGSWIDERSTAND DOORGANGSWEERSTAND	ISO/DIS 10965 ≤ 1 x 10^9 Ohm
SIZE & PACKING DIMENSION & EMBALLAGE ABMESSUNG & VERPACKUNG AFMETINGEN & VERPAKKING	50 cm x 50 cm | 19,7“ x 19,7” box: 5 m² | 5,98 yd² pallet: 20 boxes
NUMBER OF COLOURS NOMBRE DE COLORIS ANZAHL DER FARBEN AANTAL KLEUREN	10
DIMENSIONAL STABILITY STABILITÉ DIMENSIONNELLE DIMENSIONSTABILITÄT DIMENSIONELE STABILITEIT	EN 986 max. 0,2%
GUT-NR	EED994FB
LEED®	Product contributes toward satisfying Credits under LEED®.*

We reserve all rights for technical improvements | Technische wijzigingen, het verbeteren van het product, worden voorbehouden | Sous réserve de toute modification technique visant à l’amélioration constante de nos produits | Durch technische Weiterentwicklung sind Änderungen vorbehalten

* For more information, see the modulyss sustainable datasheets - Remark: Products are not reviewed under LEED®. LEED® credit requirements cover the project or building as a whole; therefore, product contribution to LEED® credits is limited. Please consult your project team for the acceptable benchmark for the design, construction, and operation of green buildings. For more information on LEED®, visit www.usgbc.org/contact.

modulyss®
Zevensterrestraat 21
B 9240 Zele
T +32 (0)52 80 80 80
F +32 (0)52 80 82 00
info@modulyss.com
www.modulyss.com